

United States Patent [19]

Yabuki et al.

[11] Patent Number: 4,888,153

[45] Date of Patent: Dec. 19, 1989

[54] FE-BASE BUILD-UP ALLOY EXCELLENT IN
RESISTANCE TO CORROSION AND WEAR

[75] Inventors: Ritsue Yabuki; Saburo Wakita, both
of Omiya, Japan

[73] Assignee: Mitsubishi Kinzoku Kabushiki
Kaisha, Tokyo, Japan

[21] Appl. No.: 219,694

[22] Filed: Jul. 7, 1988

[30] Foreign Application Priority Data

Jul. 16, 1987 [JP] Japan 62-175912

[51] Int. Cl.⁴ C22C 38/58; C22C 38/38

[52] U.S. Cl. 420/57; 420/59;
420/68; 420/66; 420/583; 420/586

[58] Field of Search 420/46, 47, 57, 59,
420/68, 583, 584, 586.1

[56] References Cited

U.S. PATENT DOCUMENTS

3,861,907 1/1975 Dulis et al. 420/59
4,086,085 4/1978 McGurty 420/46
4,430,297 2/1984 Crook 420/586.1

FOREIGN PATENT DOCUMENTS

57-16145 1/1982 Japan 420/583

Primary Examiner—Deborah Yee
Attorney, Agent, or Firm—Armstrong, Nikaido
Marmelstein, Kubovcik & Murray

[57] ABSTRACT

An Fe-base build-up alloy excellent in resistance to
corrosion and wear is disclosed. This alloy comprises in
weight percent:

C: from 0.005 to 1.6%,

Mn: from 4 to 28%,

Cr: from 12 to 36%,

Mo: from 0.01 to 9%,

Hf: from 0.005 to 15%,

N: from 0.01 to 0.9%, and

optionally contained:

Si: from 0 to 5%,

Ni: from 0 to 30%, and

one or both of:

Nb and W: from 0 to 6%, and

the balance being Fe and incidental impurities.

3 Claims, No Drawings